

# UL 19

ISBN 0-7629-0717-7

## Lined Fire Hose and Hose Assemblies

Document Was Downloaded By YAHFEI WHATI10119  
For Use By YAH FEI ELECTRIC LIGHTING CO LTD  
14083 : 6/9/2007 - 10:35 PM  
UL COPYRIGHTED MATERIAL –  
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR  
DISTRIBUTION WITHOUT PERMISSION FROM UL

Document Was Downloaded By YAHFEI WHAT110119  
For Use By YAH FEI ELECTRIC LIGHTING CO LTD  
14083 : 6/9/2007 - 10:35 PM  
UL COPYRIGHTED MATERIAL –  
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR  
DISTRIBUTION WITHOUT PERMISSION FROM UL

Underwriters Laboratories Inc. (UL)  
333 Pfingsten Road  
Northbrook, IL 60062-2096

UL Standard for Safety for Lined Fire Hose and Hose Assemblies, UL 19

Twelfth Edition, Dated November 30, 2001

As indicated on the title page (page1), this UL Standard for Safety has been adopted by the Department of Defense.

The master for this Standard at UL's Northbrook Office is the official document insofar as it relates to a UL service and the compliance of a product with respect to the requirements for that product and service, or if there are questions regarding the accuracy of this Standard.

UL's Standards for Safety are copyrighted by UL. Neither a printed copy of a Standard, nor the distribution diskette for a Standard-on-Diskette and the file for the Standard on the distribution diskette should be altered in any way. All of UL's Standards and all copyrights, ownerships, and rights regarding those Standards shall remain the sole and exclusive property of UL.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, or transmitted in any form by any means, electronic, mechanical photocopying, recording, or otherwise without prior permission of UL.

Revisions of UL Standards for Safety are issued from time to time. A UL Standard for Safety is current only if it incorporates the most recently adopted revisions.

UL provides this Standard "as is" without warranty of any kind, either expressed or implied, including but not limited to, the implied warranties of merchantability or fitness for any purpose.

In no event will UL be liable for any special, incidental, consequential, indirect or similar damages, including loss of profits, lost savings, loss of data, or any other damages arising out of the use of or the inability to use this Standard, even if UL or an authorized UL representative has been advised of the possibility of such damage. In no event shall UL's liability for any damage ever exceed the price paid for this Standard, regardless of the form of the claim.

UL will attempt to answer support requests concerning electronic versions of its Standards. However, this support service is offered on a reasonable efforts basis only, and UL may not be able to resolve every support request. UL supports the electronic versions of its Standards only if they are used under the conditions and operating systems for which it is intended. UL's support policies may change from time-to-time without notification.

UL reserves the right to change the format, presentation, file types and formats, delivery methods and formats, and the like of both its printed and electronic Standards without prior notice.

Purchasers of the electronic versions of UL's Standards for Safety agree to defend, indemnify, and hold UL harmless from and against any loss, expense, liability, damage, claim, or judgement (including reasonable attorney's fees) resulting from any error or deviation introduced while purchaser is storing an electronic Standard on the purchaser's computer system.

Document was Downloaded By YAHFER WHATI 110119  
For Use By YAH FER ELECTRIC LIGHTING CO LTD  
74083 : 6/9/2007 10:35 PM  
**UL COPYRIGHTED MATERIAL –  
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR  
DISTRIBUTION WITHOUT PERMISSION FROM UL**

If a single-user version electronic Standard was purchased, one copy of this Standard may be stored on the hard disk of a single personal computer, or on a single LAN file-server or the permanent storage device of a multiple-user computer in such a manner that this Standard may only be accessed by one user at a time and for which there is no possibility of multiple concurrent access.

If a multiple-user version electronic Standard was purchased, one copy of the Standard may be stored on a single LAN file-server, or on the permanent storage device of a multiple-user computer, or on an Intranet server. The number of concurrent users shall not exceed the number of users authorized.

Electronic Standards are intended for on-line use, such as for viewing the requirements of a Standard, conducting a word search, and the like. Only one copy of the Standard may be printed from each single-user version of an electronic Standard. Only one copy of the Standard may be printed for each authorized user of a multiple-user version of an electronic Standard. Because of differences in the computer/software/printer setup used by UL and those of electronic Standards purchasers, the printed copy obtained by a purchaser may not look exactly like the on-line screen view or the printed Standard.

An employee of an organization purchasing a UL Standard can make a copy of the page or pages being viewed for their own fair and/or practical internal use.

The requirements in this Standard are now in effect, except for those paragraphs, sections, tables, figures, and/or other elements of the Standard having future effective dates as indicated in the note following the affected item. The prior text for requirements that have been revised and that have a future effective date are located after the Standard, and are preceded by a "SUPERSEDED REQUIREMENTS" notice.

New product submittals made prior to a specified future effective date will be judged under all of the requirements in this Standard including those requirements with a specified future effective date, unless the applicant specifically requests that the product be judged under the current requirements. However, if the applicant elects this option, it should be noted that compliance with all the requirements in this Standard will be required as a condition of continued Listing and Follow-Up Services after the effective date, and understanding of this should be signified in writing.

Copyright © 2001 Underwriters Laboratories Inc.

This Standard consists of pages dated as shown in the following checklist:

Page	Date
1-38 .....	November 30, 2001

Document Was Downloaded By YAHFEI WHATI10119  
 For Use By YAH FEI ELECTRIC LIGHTING CO LTD  
 14083 : 6/9/2007 - 10:35 PM

UL COPYRIGHTED MATERIAL -  
 NOT AUTHORIZED FOR FURTHER REPRODUCTION OR  
 DISTRIBUTION WITHOUT PERMISSION FROM UL

**NOVEMBER 30, 2001**

**1**

**UL 19**

**Standard for Lined Fire Hose and Hose Assemblies**

The First through Sixth editions were titled "Cotton Rubber-Lined Hose."

First Edition – July, 1914  
Second Edition – March, 1931  
Third Edition – December, 1937  
Fourth Edition – August, 1941  
Fifth Edition – April, 1948  
Sixth Edition – August, 1953  
Seventh Edition – August, 1967  
Eighth Edition – October, 1971  
Ninth Edition – March, 1978  
Tenth Edition – December, 1992  
Eleventh Edition – December, 1995

**Twelfth Edition**

**November 30, 2001**

An effective date included as a note immediately following certain requirements is one established by Underwriters Laboratories Inc.

The Department of Defense (DoD) has adopted UL 19 on April 5, 1999. The publication of revised pages or a new edition of this Standard will not invalidate the DoD adoption.

Revisions of this Standard will be made by issuing revised or additional pages bearing their date of issue. A UL Standard is current only if it incorporates the most recently adopted revisions, all of which are itemized on the transmittal notice that accompanies the latest set of revised requirements.

**ISBN 0-7629-0717-7**

**COPYRIGHT © 1978, 2001 UNDERWRITERS LABORATORIES INC.**

Document Was Downloaded By YAHFEI WHATI10119  
For Use By YAH FEI ELECTRIC LIGHTING CO LTD  
14083 : 6/9/2007 - 10:35 PM  
UL COPYRIGHTED MATERIAL –  
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR  
DISTRIBUTION WITHOUT PERMISSION FROM UL

No Text on This Page

Document Was Downloaded By YAHFEI WHATI10119  
For Use By YAH FEI ELECTRIC LIGHTING CO LTD  
14083 : 6/9/2007 - 10:35 PM  
UL COPYRIGHTED MATERIAL –  
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR  
DISTRIBUTION WITHOUT PERMISSION FROM UL

## CONTENTS

FOREWORD .....	8
----------------	---

## INTRODUCTION

1 Scope .....	9
2 General .....	9
2.1 Units of measurement .....	9
2.2 Undated references .....	9
3 Glossary .....	9

## CONSTRUCTION

4 Length .....	10
5 Internal Diameter .....	10
6 Jacket and Inner Reinforcements .....	10
7 Lining .....	11
8 Cover .....	11
9 Coatings and Treatments .....	11
10 Couplings .....	11

## PERFORMANCE

11 Hydrostatic Proof-Pressure Tests .....	12
11.1 General .....	12
11.2 Sample .....	13
11.3 Equipment .....	13
11.4 Test method .....	13
12 Kink Test .....	15
12.1 General .....	15
12.2 Sample .....	15
12.3 Equipment .....	15
12.4 Test method .....	15
13 Hydrostatic Strength Test .....	15
13.1 General .....	15
13.2 Sample .....	16
13.3 Equipment .....	16
13.4 Test method .....	16
14 Repeated Bending Test .....	16
14.1 General .....	16
14.2 Sample .....	16
14.3 Equipment .....	17
14.4 Test method .....	18
15 Alternating Pressure Test .....	18
15.1 General .....	18
15.2 Sample .....	18
15.3 Equipment .....	18
15.4 Test method .....	19
16 Abrasion Test .....	19
16.1 General .....	19
16.2 Sample .....	19

UL COPYRIGHTED MATERIAL -  
 NOT AUTHORIZED FOR FURTHER REPRODUCTION OR  
 DISTRIBUTION WITHOUT PERMISSION FROM UL

Document was Downloaded By YAHFEI WHATI10119  
 FOR Use By YAH FEI ELECTRIC LIGHTING CO LTD  
 74083 : 6/9/2007 . 10:35 PM

16.3	Equipment	19
16.4	Test method	20
17	Heat-Resistance Test	20
17.1	General	20
17.2	Sample	20
17.3	Equipment	20
17.4	Test method	20
18	Fold-Resistance Test	21
18.1	General	21
18.2	Sample	21
18.3	Equipment	21
18.4	Test method	21
19	Wet Hose Test	21
19.1	General	21
19.2	Sample	22
19.3	Test method	22
20	Low-Temperature Test	22
20.1	General	22
20.2	Sample	22
20.3	Equipment	22
20.4	Test method	22
21	Coupling Retention Test	23
21.1	General	23
21.2	Sample	23
21.3	Equipment	23
21.4	Test method	23
22	Friction Loss Test	23
22.1	General	23
22.2	Sample	24
22.3	Equipment	24
22.4	Test method	24
23	Accelerated Aging Test of Threads	24
23.1	General	24
23.2	Sample	24
23.3	Equipment	25
23.4	Test method	25
24	Adhesion Tests	25
24.1	General	25
24.2	Sample	26
24.3	Equipment	26
24.4	Test method	26
25	Accelerated Aging Test of Linings and Covers	26
25.1	General	26
25.2	Sample	27
25.3	Equipment	27
25.4	Test method	27
26	Ozone-Exposure Test of Linings and Covers	28
26.1	General	28
26.2	Sample	28
26.3	Equipment	29
26.4	Test method	29
27	Water Immersion Test of Linings	29
27.1	General	29

UL COPYRIGHTED MATERIAL -  
 NOT AUTHORIZED FOR FURTHER REPRODUCTION OR  
 DISTRIBUTION WITHOUT PERMISSION FROM UL

Document was Downloaded By YAHFEI WHA110119  
 For Use By YAH FEI ELECTRIC LIGHTING CO LTD  
 74083 : 6/9/2007 10:35 PM

27.2 Sample ..... 29

27.3 Equipment ..... 30

27.4 Method – Effect on tensile strength and ultimate elongation ..... 30

27.5 Method – Effect on volume ..... 30

28 Pull Test ..... 31

28.1 General ..... 31

28.2 Sample ..... 31

28.3 Test method ..... 31

29 Accelerated Aging Test of Hose Assembly ..... 31

29.1 General ..... 31

29.2 Sample ..... 31

29.3 Equipment ..... 31

29.4 Test method ..... 32

30 Rough Usage Test ..... 32

30.1 General ..... 32

30.2 Sample ..... 32

30.3 Equipment ..... 32

30.4 Test method ..... 32

31 Moist Ammonia-Air Stress Cracking Test ..... 32

31.1 General ..... 32

31.2 Sample ..... 33

31.3 Equipment ..... 33

31.4 Method ..... 33

32 Salt-Spray Corrosion Test ..... 33

32.1 General ..... 33

32.2 Sample ..... 34

32.3 Equipment ..... 34

32.4 Test method ..... 34

33 Accelerated Aging Test of Gaskets ..... 34

33.1 General ..... 34

33.2 Sample ..... 34

33.3 Equipment ..... 35

33.4 Test method ..... 35

34 Compression Set Test ..... 35

34.1 General ..... 35

34.2 Samples ..... 35

34.3 Equipment ..... 35

34.4 Test method ..... 35

35 Ozone Resistance Test of Gaskets ..... 35

35.1 General ..... 35

35.2 Sample ..... 36

35.3 Equipment ..... 36

35.4 Test method ..... 36

36 Water Immersion Test of Gaskets ..... 36

36.1 General ..... 36

36.2 Sample ..... 36

**MANUFACTURING AND PRODUCTION TESTS**

37 General ..... 36

Document Was Downloaded By YAHFEI WHAT110119  
 For Use By YAH FEI ELECTRIC LIGHTING CO LTD  
 14083 : 6/9/2007 - 10:35 PM  
**UL COPYRIGHTED MATERIAL –**  
**NOT AUTHORIZED FOR FURTHER REPRODUCTION OR**  
**DISTRIBUTION WITHOUT PERMISSION FROM UL**

**MARKING**

38 Details ..... 37  
    38.1 General ..... 37  
    38.2 Hose ..... 37  
    38.3 Hose Assemblies ..... 37

Document Was Downloaded By YAHFEI WHATI10119  
For Use By YAH FEI ELECTRIC LIGHTING CO LTD  
14083 : 6/9/2007 - 10:35 PM  
UL COPYRIGHTED MATERIAL –  
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR  
DISTRIBUTION WITHOUT PERMISSION FROM UL

No Text on This Page

Document Was Downloaded By YAHFEI WHATI10119  
For Use By YAH FEI ELECTRIC LIGHTING CO LTD  
14083 : 6/9/2007 - 10:35 PM  
UL COPYRIGHTED MATERIAL -  
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR  
DISTRIBUTION WITHOUT PERMISSION FROM UL

## FOREWORD

A. This Standard contains basic requirements for products covered by Underwriters Laboratories Inc. (UL) under its Follow-Up Service for this category within the limitations given below and in the Scope section of this Standard. These requirements are based upon sound engineering principles, research, records of tests and field experience, and an appreciation of the problems of manufacture, installation, and use derived from consultation with and information obtained from manufacturers, users, inspection authorities, and others having specialized experience. They are subject to revision as further experience and investigation may show is necessary or desirable.

B. The observance of the requirements of this Standard by a manufacturer is one of the conditions of the continued coverage of the manufacturer's product.

C. A product which complies with the text of this Standard will not necessarily be judged to comply with the Standard if, when examined and tested, it is found to have other features which impair the level of safety contemplated by these requirements.

D. A product that contains features, characteristics, components, materials, or systems new or different from those covered by the requirements in this standard, and that involves a risk of fire or of electric shock or injury to persons shall be evaluated using appropriate additional component and end-product requirements to maintain the level of safety as originally anticipated by the intent of this standard. A product whose features, characteristics, components, materials, or systems conflict with specific requirements or provisions of this standard does not comply with this standard. Revision of requirements shall be proposed and adopted in conformance with the methods employed for development, revision, and implementation of this standard.

E. UL, in performing its functions in accordance with its objectives, does not assume or undertake to discharge any responsibility of the manufacturer or any other party. The opinions and findings of UL represent its professional judgment given with due consideration to the necessary limitations of practical operation and state of the art at the time the Standard is processed. UL shall not be responsible to anyone for the use of or reliance upon this Standard by anyone. UL shall not incur any obligation or liability for damages, including consequential damages, arising out of or in connection with the use, interpretation of, or reliance upon this Standard.

F. Many tests required by the Standards of UL are inherently hazardous and adequate safeguards for personnel and property shall be employed in conducting such tests.

Document Was Downloaded By YAHFEI WHATI10119  
For Use By YAH FEI ELECTRIC LIGHTING CO LTD  
14083 : 6/9/2007 - 10:35 PM  
UL COPYRIGHTED MATERIAL –  
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR  
DISTRIBUTION WITHOUT PERMISSION FROM UL

## INTRODUCTION

### 1 Scope

1.1 These requirements cover single- and multiple-jacketed lined fire hose with or without couplings attached, in the trade sizes of 1-1/2, 1-3/4, 2, 2-1/2, 3, 3-1/2, 4, 5, and 6 inch (38, 45, 51, 65, 76, 89, 102, 127, and 152 mm nominal ID). Single-jacketed hose is intended for service test pressures of 150, 200, or 250 psig (1035, 1380, or 1725 kPa). Multiple-jacketed hose or covered hose judged equivalent to multiple-jacketed hose is intended for service test pressures of 200, 300, or 400 psig (1380, 2070, or 2760 kPa).

1.2 These products are intended for municipal and industrial fire protection purposes. Single-jacketed hose is for use at fire hydrants, standpipes, and similar places. They are not intended for hard usage nor where the hose will be subjected to chafing on rough or sharp surfaces. Multiple-jacketed hose or covered hose judged equivalent to multiple-jacketed hose are for use on pumpers and in places where service conditions require the additional protection against wear afforded by the extra woven jacket or cover.

1.3 The products covered by these requirements are intended to be periodically inspected and maintained while in service, as outlined in the Standard for the Care, Use, and Service Testing of Fire Hose Including Couplings and Nozzles, NFPA 1962.

### 2 General

#### 2.1 Units of measurement

2.1.1 Values stated without parentheses are the requirement. Values in parentheses are explanatory or approximate information.

#### 2.2 Undated references

2.2.1 Any undated reference to a code or standard appearing in the requirements of this standard shall be interpreted as referring to the latest edition of that code or standard.

### 3 Glossary

3.1 For the purpose of this standard, the following definitions apply.

3.2 EXPANSION RING – A ring that expands against the hose lining, forcing the hose tightly against the coupling.

3.3 FILLER THREADS – The threads or yarns of the jacket or reinforcement that are helically wound throughout the length of the hose at approximately right angles to the warp threads.

3.4 HOSE ASSEMBLY – Hose furnished with couplings attached to each end.

3.5 MULTIPLE-JACKETED HOSE – Hose having two or more woven jackets or a covered hose that complies with all of the performance tests in this standard for multiple-jacketed hose. See 6.3.

3.6 PROOF PRESSURE – A specified pressure applied to new hose to indicate its acceptability at intended maximum normal highest operating pressures.

3.7 SERVICE TEST PRESSURE – The pressure to which the hose is periodically tested to determine that it can remain in service. The service test pressure is at least 10 percent greater than the maximum normal highest operating pressure.

3.8 WARP THREADS – The threads or yarns of the jacket or reinforcement that run lengthwise to the hose.

## CONSTRUCTION

### 4 Length

4.1 Unless otherwise specified, the hose shall be in nominal 50- to 100-foot (15.2 – 30.5 m) lengths. The length of the hose is the measurement obtained as described in 11.4.3 – 11.4.5.

### 5 Internal Diameter

5.1 Hose shall have an internal diameter of not less than the trade size of the hose.

5.2 A tapered plug gauge having a taper of 3/8 inch per foot (31.2 mm/m) marked to indicate variations of 1/64 inch (0.4 mm) in diameter, is to be used to measure the internal diameter. If the lining of the hose has a lap joint, the tapered plug gauge is to be provided with a slot to accommodate the lap joint.

5.3 To determine the internal diameter, the end of the hose is to be cut square and the tapered plug gauge inserted in the hose sample until a close fit is obtained without forcing. The diameter of the gauge at the end of the sample, to the nearest 1/64 inch (0.4 mm), is to be recorded as the internal diameter of the hose.

### 6 Jacket and Inner Reinforcements

6.1 A jacket shall be evenly and firmly woven, and free from visible defects, thread knots, lumps, and irregularities of twist provided that they would not impair its intended use. The threads shall be continuous, and any knots in the filler threads shall be tucked under the warp threads.

6.2 A jacket shall be seamless and shall have the fillers woven around the hose throughout its length and the warps interwoven with the fillers. A jacket may be made with a cover over the woven jacket.

6.3 Hose having a woven jacket or hose having an inner reinforcement and a protective cover may be considered equivalent to multiple-jacketed hose if it complies with the applicable performance requirements specified in this standard.

## 7 Lining

7.1 A lining shall be of uniform thickness and free from pitting or other irregularities or imperfections and shall comply with the applicable test requirements specified in Sections 24 – 27.

## 8 Cover

8.1 A cover shall be of uniform thickness and free from pitting, blisters, or other imperfections that would impair its intended use, and shall comply with the applicable test requirements in Sections 24 – 26.

8.2 A cover may have intentional pricking, ribs, corrugations, or a wrapped finish.

## 9 Coatings and Treatments

9.1 Hose may have jackets with treatments or coatings if the hose complies with the applicable performance requirements in this standard.

## 10 Couplings

10.1 The couplings of hose assemblies shall be made from metals having the strength and other characteristics necessary to comply with the applicable performance requirements in this standard.

10.2 A metal used in the construction of any part shall have corrosion-resistant properties equivalent to those of high-strength yellow brass, UNS No. C86500 in the Standard Specification for Copper Alloys in Ingot form, ASTM B30 and in the Standard Specification for Copper Alloy Sand Castings for General Applications, ASTM B584.

10.3 To determine if a metal has the properties mentioned in 10.2, it shall comply with the requirements of the Salt-Spray Corrosion Test, Section 32.

10.4 A copper-alloy part containing more than 15 percent zinc shall comply with the requirements of the Moist Ammonia Air-Stress Cracking Test, Section 31.

10.5 An expansion ring of a coupling shall be smooth and have rounded edges.

10.6 A swivel mechanism of a coupling shall turn freely by hand.

10.7 A surface shall have no sharp edges or projections that might abrade a hose. The inside surfaces shall be machine-finished.

*Exception: Corrugations in a tail section need not be machine-finished.*

10.8 A gasket of a coupling shall have uniform dimensions.

## PERFORMANCE

### 11 Hydrostatic Proof-Pressure Tests

#### 11.1 General

11.1.1 Hose shall comply with items a – h and hose assemblies shall comply with items a – l, when subjected for at least 15 seconds to a hydrostatic proof-pressure of two times the service pressure. The pressure may be maintained for up to 1 minute if necessary, to determine compliance with the requirements. See 11.4.5.

- a) The elongation of single-jacketed hose shall not exceed 10 percent of the length measured at 10 psig (69 kPa). See 11.4.6.
- b) The elongation of multiple-jacketed hose shall not exceed 8 percent of the length measured at 10 psig for sizes of 1-1/2 – 2-1/2 inches (38 – 65 mm nominal ID). See 11.4.6.
- c) The elongation of multiple-jacketed hose shall not exceed 10 percent of the length measured at 10 psig for sizes of 3 inches (76 mm nominal ID). See 11.4.6.
- d) The elongation of multiple-jacketed hose shall not exceed 13 percent of the length measured at 10 psig for sizes of 3-1/2 – 6 inches (89 – 152 mm nominal ID). See 11.4.6.
- e) The hose shall not leak or balloon, and there shall be no breaking of any thread in the jacket.
- f) The twist of the hose shall not exceed the values indicated in Table 11.1. Any final twist shall be in the direction to tighten couplings. A twist to the right, the direction that would tend to tighten couplings, is indicated by a clockwise rotation of the free end of the hose as viewed from the water supply end. The hose shall not twist to the left more than 2 degrees per foot (0.114 rad/m) while the pressure is being increased to the test value. See 11.4.7.
- g) The warp of the hose shall not exceed 20 inches (508 mm) per 50 foot (15.2 m) length. See 11.4.8 and 11.4.9.
- h) Single-jacketed hose shall not rise from the level of the test surface more than 7 inches (178 mm) for hose sizes of 1-1/2 – 2 inches (38 – 51 mm nominal ID). See 11.4.11.
- i) Single-jacketed hose shall not rise from the level of the test surface more than 4 inches (102 mm) for hose sizes of 2-1/2 and 3 inches (65 and 76 mm nominal ID). See 11.4.11.
- j) Single-jacketed hose shall not rise from the test surface for hose sizes of 3-1/2 inches (89 mm) and larger. See 11.4.11.
- k) Multiple-jacketed hose shall not rise from the test surface. See 11.4.11.
- l) A hose assembly shall show no slippage or leakage of the coupling or damage to the hose at the coupling.

## 11.2 Sample

11.2.1 The test is to be conducted on a nominal 50 foot (15.2 m) length or longer, unless otherwise specified, sample of the hose or hose assembly.

## 11.3 Equipment

11.3.1 A hand- or power-driven pump or an accumulator system capable of increasing the pressure in the sample at a rate of 300 – 1000 psig (2070 – 6900 kPa) per minute is to be used.

11.3.2 The test surface is to be inclined to facilitate removal of air from the sample and of such design and dimensions that the sample is free to move during the tests.

**Table 11.1**  
**Maximum twist of hose per 50 feet**

Trade size of hose, Inches, (mm ID)	No. of jackets	Service test pressure, psi (kPa)	Maximum twist, turns per 50 feet (15.2 m)
1-1/2, 1-3/4, 2 (38, 45, 51)	Single	150 (1035)	7-1/2
2-1/2, 3, 3-1/2, 4, 5, 6 (65, 76, 89, 102, 127, 152)	Single	150 (1035)	3-3/4
1-1/2, 1-3/4, 2 (38, 45, 51)	Single	200 or 250 (1380 or 1725)	10
2-1/2, 3, 3-1/2, 4, 5, 6 (65, 76, 89, 102, 127, 152)	Single	250 (1725)	5
1-1/2, 2 (38, 51)	Multiple	200, 300, or 400 (1380, 2070, or 2760)	4-1/4
2-1/2, 3, 3-1/2, 4, 5, 6 (65, 76, 89, 102, 127, 152)	Multiple	200, 300, or 400 (1380, 2070, or 2760)	1-3/4

## 11.4 Test method

11.4.1 If a hose assembly is being tested, it is to be marked prior to the tests with a pencil or other suitable means at a point immediately adjacent to each coupling.

11.4.2 One end of the sample is to be connected to the source of water supply by means of couplings or temporary test fittings, and the other end is to be free to move and is to be closed by a fitting provided with a petcock for the escape of air while the sample is being filled with water. For hose having a nominal length of 50 feet (15.2 m), the connection between the end of the sample and the source of water supply is to be rigid. For hose having a nominal length greater than 50 feet, the connection between the end of the sample and the source of water supply may be flexible.

11.4.3 The sample is to be stretched out on the test surface so as to lie straight and without twist. To facilitate the complete removal of air from the sample, the surface on which the sample rests is to be inclined so that the supply end is lower than the other end. With the petcock open, water is to be admitted through the sample gradually until all air has been expelled and the sample is completely filled with water. The petcock is then to be closed and the pressure raised to 10 psig (69 kPa) and held at that pressure

while the initial length measurement is taken. While at this pressure, the sample is to be straightened out in order to obtain an accurate measurement. The jacket construction and workmanship in weaving, particularly knots, loose ends, and skips in warp threads are to be noted and recorded.

11.4.4 The length of the sample between fittings is to be measured and recorded to the nearest inch (centimeter). The position of the sample with regard to twist is to be noted. From this point on, neither the sample nor the fittings are to be touched, moved, or interfered with in any way until all measurements and observations have been completed at the final test pressure.

11.4.5 Following measurement of the length at 10 psig (69 kPa), the pressure in the sample is to be increased at a rate of 300 – 1000 psig (2070 – 6900 kPa) per minute until the required proof pressure is reached. While the pressure is being increased, the sample is to be examined for leakage and other defects. The proof pressure is to be maintained for at least 15 seconds, but not more than 1 minute. During the time the test pressure is maintained, the observations and measurements for elongation, twist, warp, and rise are to be completed.

11.4.6 If the sample warps to any appreciable extent and particularly if the allowable limit of elongation is approached, the length at proof pressure is to be measured by following the contour of the sample. For samples that do not warp to any extent, the measurement is to be taken parallel to the edge of the test surface. For this purpose, an edge of the table is to be marked off in feet and inches (meters and centimeters). All measurements are to be taken to the nearest inch (centimeter) from the inside edges of the fittings. The elongation of the sample is to be calculated from the measurement taken at the proof pressure and the measurement taken at 10 psi (69 kPa).

11.4.7 The amount of twist at proof pressure is to be measured by following the color line or by noting, in the period during which the pressure is being applied, the turns of the fitting at the free end of the sample. The amount of twist is to be recorded to the nearest one-eighth turn or 45 degrees (0.79 rad), and the direction as either right or left.

11.4.8 For samples having a nominal length of 50 feet (15.2 m), or less if specified, the warp is the maximum deviation between the sample and a straight line that is drawn between reference points on the fittings at each end of the sample.

11.4.9 For samples having a length greater than 50 feet (15.2 m) but not exceeding 100 feet (30.5 m), the warp is the maximum deviation between the sample and each of two straight lines. One straight line is to be drawn between the reference point on one fitting to a reference point on the sample 50 feet from that fitting. The other straight line is to be drawn from the reference point on the other fitting to a reference point on the sample 50 feet from that fitting. All reference points are to be located on the centerline of the sample and the center of the fittings.

11.4.10 If a hose is not provided with a fitting at its free end, a lightweight fitting without lugs is to be attached to the free end. If a fitting with lugs is provided on the free end of the hose, an adaptor that does not weigh more than the fitting and that has a larger outside diameter than the lugs is to be attached to the fitting.

11.4.11 The maximum distance that the sample rises above the test surface while at the proof pressure is to be measured to the nearest inch (centimeter).

## 12 Kink Test

### 12.1 General

12.1.1 Hose and hose assemblies, while kinked, shall withstand a hydrostatic test pressure of 1-1/2 times the marked service test pressure without leakage, rupturing, or breaking of any thread in the jacket or reinforcement.

### 12.2 Sample

12.2.1 The length of the sample is to be at least 3 feet (0.9 m).

### 12.3 Equipment

12.3.1 The hydrostatic equipment for this test is to be the same as that specified in 11.3.1.

### 12.4 Test method

12.4.1 The sample is to be filled with water with the petcock open to allow all air to escape. The petcock is then to be closed, the pressure raised to approximately (but not exceeding) 10 psig (69 kPa), and the sample kinked 18 inches (457 mm) from the free end by tying the hose back against itself as close to the fittings as practicable, so that there will be a sharp kink. The pressure is then to be increased at a rate of 300 – 1000 psig (2070 – 6900 kPa) per minute until 1-1/2 times the service test pressure is reached, and then immediately released.

## 13 Hydrostatic Strength Test

### 13.1 General

13.1.1 Hose, while lying straight, and curved around a surface having a radius of 27 inches (0.7 m), shall withstand a hydrostatic test pressure of three times the marked service test pressure without rupturing or breaking of any thread in the jacket or reinforcement.

13.1.2 Hose assemblies, while lying straight, and curved around a surface having a radius of 27 inches (0.7 m), shall withstand a hydrostatic test pressure of three times the service test pressure without leakage, rupturing, or breaking of any thread in the jacket or reinforcement, and without slippage, leakage, or damage of the couplings.

## 13.2 Sample

13.2.1 The length of the sample is to be 3 feet (0.9 m).

13.2.2 If a hose assembly is being tested, the sample is to be marked prior to the test with a pencil or other suitable means at a point immediately adjacent to each coupling.

## 13.3 Equipment

13.3.1 The hydrostatic equipment for this test is to be the same as that described in 11.3.1, except that a protective enclosure is also to be used.

13.3.2 A test frame or surface that is curved to a radius of 27 inches (0.7 m) is to be used for conducting the burst test while the hose is in the curved position. The test frame on the surface is to have provisions for firmly securing both ends of the sample while under test.

## 13.4 Test method

13.4.1 The sample is to be placed in a protective enclosure, connected to the source of water supply, the air expelled, and the pressure raised at a rate of 300 – 1000 psig (2070 – 6900 kPa) per minute until the hydrostatic test pressure specified in 13.1.1 or 13.1.2 is reached, and immediately released. The sample is to be tested in the straight and curved positions.

## 14 Repeated Bending Test

### 14.1 General

14.1.1 A coupled sample of hose in the sizes of 1-1/2, 1-3/4, 2, 2-1/2, 3, and 3-1/2 inches (38, 45, 51, 65, 76, and 89 mm nominal ID) shall withstand 100,000 cycles of repeated bending to the radius specified in Table 14.1, while filled with water, without breakdown. Upon completion of the repeated bending, the sample, while lying straight, shall comply with the requirements of the Hydrostatic Strength Test, Section 13.

### 14.2 Sample

14.2.1 The length of sample as specified in Table 14.2 is to be used.

**Table 14.1**  
**Radius of bend and distance between center of reels for repeated bending test**

Trade size of hose,		Radius of bending,		Distance between centers of reels, Inches (mm)			
Inches	(mm ID)	Inches	(mm)	Vertical		Horizontal	
1-1/2	(38)	8	(203)	19	(483)	8	(203)
1-3/4	(45)						
2	(51)	14	(356)	34	(864)	14	(356)
2-1/2	(65)						
3	(76)	16	(406)	34	(864)	14	(356)
3-1/2	(76)						

**Table 14.2**  
**Length of test sample for repeated bending test**

Trade size of hose,		Length of test sample,	
Inches	(mm ID)	feet	(m)
1-1/2	(38)	14	(4.3)
1-3/4	(45)		
2	(51)	15	(4.6)
2-1/2	(65)		
3	(76)	16	(4.9)
3-1/2	(89)		

### 14.3 Equipment

14.3.1 The equipment for this test is to consist of a steel framework on which are mounted two wooden reels. A semicircular groove, wide enough to accommodate the sample without binding, is to be cut in the circumference of each reel to act as a guide for the sample. The radius of the reels, measured to the base of the circumferential grooves, is to be as specified in Table 14.1. The reels are to be mounted with their flat sides in the same vertical plane so that the distance between centers is as specified in Table 14.1. Each reel is to rotate freely about an axle at its center. A motor-driven mechanism is to be provided that pulls the sample up over the reels for a total distance of approximately 4 feet (1.2 m) and then reverses to let the hose down, at a rate of  $4 \pm 1$  complete cycles per minute.

## 14.4 Test method

14.4.1 The sample is to be filled with water and capped at each end. It is then to be placed over the reels in an S-shaped curve with the end that passes over the top reel brought down and a weight just sufficient to make the sample conform to the reels is to be attached. The end that passes under the bottom reel is to be brought up and fastened to the motor-driven mechanism described in 14.3.1. The sample is to be subjected to 100,000 complete cycles of bending.

14.4.2 After completion of the bending, the sample is to be removed from the test equipment, examined for any evidence of damage, and then tested in accordance with the Hydrostatic Strength Test, Section 13, while the sample is lying straight. In lieu of subjecting the entire length to the burst test, a 3 foot or longer section can be cut from the central portion of hose that received bending in two directions, recoupled, and then subjected to the Hydrostatic Strength Test.

## 15 Alternating Pressure Test

### 15.1 General

15.1.1 Hose and hose assemblies shall withstand 2000 cycles of alternating low and high pressure, between 0 psig and the service test pressure, without breakdown. After cycling, the sample shall withstand the appropriate proof-pressure in Section 11, without leakage, ballooning or rupture.

### 15.2 Sample

15.2.1 The length of the sample is to be 12 feet (3.7 m).

15.2.2 If a hose assembly is being tested, the sample is to be marked prior to the test with a pencil or other suitable means at a point immediately adjacent to each coupling.

### 15.3 Equipment

15.3.1 The equipment for this test is to consist of a pump as described in 11.3.1, capable of increasing the internal pressure from 0 psig to the sample's service test pressure and means to decrease the internal pressure of the sample to 0 psig, at a rate of  $3 \pm 1/2$  cycles of pressure change per minute.

## 15.4 Test method

15.4.1 The sample is to be connected to the source of water under pressure, the air expelled, and the hydrostatic pressure within the sample alternately raised to the service test pressure and then lowered to 0 psig. The rate of increase and decrease is to be uniform and such that approximately 20 seconds are required to go from 0 psig to the maximum test pressure and back to 0 psig (1 cycle).

15.4.2 After completion of 2000 cycles of low and high pressure, the sample is to be subjected to the appropriate proof-pressure in Section 11.

## 16 Abrasion Test

### 16.1 General

16.1.1 Hose shall withstand 1-1/2 times the service test pressure without rupturing or breaking any thread in the jacket or reinforcement, after 300 cycles of abrasion for single-jacketed hose and after 500 cycles of abrasion for multiple-jacketed hose.

### 16.2 Sample

16.2.1 The length of the sample is to be 5 to 7 feet (1.5 to 2.1 m).

### 16.3 Equipment

16.3.1 The following equipment is to be used:

- a) A horizontally reciprocating machine with a 12 inch (305-mm) stroke capable of 20 cycles per minute.
- b) A stationary mandrel having a diameter of 2-1/4 inches (57.2 mm) and covered with No. 1-1/2 (coarse) emery cloth.
- c) An 8 pound (3.6 kg) weight for 1-1/2, 1-3/4, and 2 inch (38, 45, and 51 mm nominal ID) size hose.
- d) A 12 pound (5.4 kg) weight for 2-1/2 and 3 inch (65 and 76 mm nominal ID) size hose.
- e) A 15 pound (6.8 kg) weight for 3-1/2 and 4 inch (89 and 102 mm) size hose.
- f) An 18 pound (8.2 kg) weight for sizes greater than 4 inches (102 mm).
- g) The hydrostatic equipment specified in 11.3.1 and a protective enclosure.

## 16.4 Test method

16.4.1 The sample is to be clamped at one end to a horizontally reciprocating crossbar. The other end is to be allowed to hang down over the mandrel. The appropriate weight specified in 16.3.1 is to be attached to the free end of the sample. Coupled hose samples may be used for this test, but the total weight at the end of the hose, including the weight of the coupling, expansion ring, and any adapters or clamps, is to equal the weight given in 16.3.1.

16.4.2 The sample is to be drawn back and forth over the emery cloth at a rate of  $20 \pm 2$  cycles per minute by the motion of the crossbar. At the end of each 50 cycles, the emery cloth is to be cleaned by means of compressed air. New emery cloth is to be used for each test sample. After the applicable number of cycles specified in 16.1.1, the sample is to be removed from the test apparatus, coupled if necessary, connected to the source of water supply, the air expelled, and the pressure raised at a rate of 300 – 1000 psig (2.07 – 6.89 MPa) per minute until 1-1/2 times the service test pressure is reached.

## 17 Heat-Resistance Test

### 17.1 General

17.1.1 A coupled sample of hose, while lying straight, shall comply with the requirements of the Hydrostatic Strength Test, Section 13, after exposure to a heated steel block, as described in 17.4.1.

### 17.2 Sample

17.2.1 The length of the sample is to be 18 inches (457 mm).

### 17.3 Equipment

17.3.1 An oven capable of maintaining a temperature of  $260.0 \pm 1.0^\circ\text{C}$  ( $500.0 \pm 1.8^\circ\text{F}$ ), a steel block 2-1/2 by 1-1/2 by 8 inches (63.5 by 38 by 203 mm), the hydrostatic equipment specified in 11.3.1, and a protective enclosure are to be used for this test.

### 17.4 Test method

17.4.1 The sample is to be sealed at one end, filled with tap water, sealed at the other end, and conditioned for 24 hours in a room maintained at  $23.0 \pm 2.0^\circ\text{C}$  ( $73.0 \pm 3.6^\circ\text{F}$ ). The steel block is to be heated for at least 16 hours in an oven maintained at  $260.0 \pm 1.0^\circ\text{C}$  ( $500.0 \pm 1.8^\circ\text{F}$ ), removed from the oven, and within 5 seconds placed so that the longitudinal axis of the steel block is perpendicular to the longitudinal axis of the sample. The contact area is to be the midpoint of the 2-1/2 inch (63.5 mm) wide side of the steel block and the midpoint of the sample. A metal knife edge is to be used as a support near one end of the steel block to balance the steel block and obtain maximum force on the hose. After 60 seconds, the steel block is to be removed. After the hose has cooled, it is to be laid straight and subjected to the Hydrostatic Strength Test, Section 13.

## 18 Fold-Resistance Test

### 18.1 General

18.1.1 Hose, while lying straight, shall comply with the requirements of the Hydrostatic Strength Test, Section 13, after being subjected to folding described in 18.4.1.

### 18.2 Sample

18.2.1 The length of the sample is to be 3 feet (0.9 m).

### 18.3 Equipment

18.3.1 Equipment for this test is to consist of a Type II A oven as described in the Standard Specification for Gravity – Convection and Forced-Ventilation Ovens, ASTM E145, a clamp fitted with calibrated springs capable of exerting a total force of 120 pounds (534 N), the equipment specified in 11.3, and a protective enclosure.

### 18.4 Test method

18.4.1 The sample is to be folded at the center of the length and held tightly folded by means of a clamp fitted with calibrated springs so that a total force of 120 pounds (534 N) is exerted on the fold. The assembly is then to be placed in a thermostatically controlled oven maintained at a temperature of  $60 \pm 1^\circ\text{C}$  ( $140.0 \pm 1.8^\circ\text{F}$ ), for 30 days. At the end of the test period, the assembly is to be removed from the oven and allowed to cool at room temperature. The clamp is then to be removed, and the sample is to be laid straight and subjected to the Hydrostatic Strength Test, Section 13. If the lining of the hose adheres to itself after the clamp is removed, the lining shall free itself by the time the service test pressure is reached during the Hydrostatic Strength Test.

## 19 Wet Hose Test

### 19.1 General

19.1.1 Hose and hose assemblies shall withstand 48 hours of immersion in water at room temperature without visible deterioration and shall then comply with the requirements of the Hydrostatic Strength Test, Section 13, while wet and lying straight.

## 19.2 Sample

19.2.1 The length of the sample is to be 3 feet (0.9 m).

## 19.3 Test method

19.3.1 A sample is to be immersed in tap water at room temperature for 48 hours. The sample is then to be removed from the water and subjected to the Hydrostatic Strength Test, Section 13.

## 20 Low-Temperature Test

### 20.1 General

20.1.1 Hose not marked in accordance with 38.2.2 shall withstand the appropriate proof-pressure in Section 11, without leakage, ballooning, or rupture, after being subjected to cold flexing at a temperature of minus  $4.0 \pm 1.8^\circ\text{F}$  (minus  $20.0 \pm 1.0^\circ\text{C}$ ) as described in 20.4.1.

20.1.2 Hose marked in accordance with 38.2.2 shall withstand the appropriate proof-pressure in Section 11, without leakage, ballooning or rupture, after being subjected to cold flexing at a temperature of minus  $65.0 \pm 1.8^\circ\text{F}$  (minus  $54.0 \pm 1.0^\circ\text{C}$ ) as described in 20.4.1.

### 20.2 Sample

20.2.1 The length of the sample is to be 3 feet (0.9 m).

### 20.3 Equipment

20.3.1 The equipment for this test is to consist of that specified in 11.3.1, a protective enclosure, and a cold box capable of maintaining the appropriate temperature and of sufficient capacity to accommodate the test samples.

### 20.4 Test method

20.4.1 The sample is to be placed in a container of water at room temperature for  $24 \pm 1/2$  hours. The sample is then to be removed from the water, exposed to room temperature for 15 minutes, and then placed in the cold box maintained at the appropriate test temperature. After  $16 \pm 1-1/2$  hours in the cold box, the sample is to be removed and immediately bent double on itself (180 degrees), first one way and then the other. The sample is then to be thawed at room temperature for 24 hours, laid straight, and subjected to the proof-pressure in Section 11.

## 21 Coupling Retention Test

### 21.1 General

21.1.1 Hose assemblies shall withstand a hydrostatic proof-pressure of two times the service test pressure for 10 minutes without slippage or leakage of the couplings or damage to the hose at the couplings.

### 21.2 Sample

21.2.1 The length of the sample is to be 3 feet (0.9 m).

### 21.3 Equipment

21.3.1 The equipment specified in 11.3.1 and 11.3.2 and a protective cover are to be used for this test.

### 21.4 Test method

21.4.1 The sample is to be marked prior to the test with a pencil or other suitable means at a point immediately adjacent to each coupling. The sample is then to be placed in the protective enclosure, connected to the source of water supply, the air expelled, and the pressure raised at a rate of 300 – 1000 psig (2070 – 6900 kPa) per minute until the appropriate proof-pressure is reached. After 10 minutes at the test pressure, the sample assembly is to be examined for slippage, leakage, or damage to the hose at the couplings.

## 22 Friction Loss Test

### 22.1 General

22.1.1 A hose shall not have a friction loss greater than the values specified in Table 22.1.

**Table 22.1**  
**Maximum friction loss of hose**

Trade size of hose, Inches (mm ID)		Flow rate gallons (L) per minute		Maximum acceptable friction loss per 100 feet (30.5 m) of hose, psig (kPa)	
1-1/2	(38)	120	(454.2)	45.0	(310)
1-3/4	(45)	120	(454.2)	30.0	(207)
2	(51)	150	(567.8)	20.0	(138)
2-1/2	(65)	220	(832.7)	12.0	(83)
3	(76)	400	(1514.0)	15.0	(103)
3-1/2	(89)	600	(2271.0)	15.0	(103)

## 22.2 Sample

22.2.1 The length of the sample is to be at least 50 feet (15 m).

## 22.3 Equipment

22.3.1 The following equipment is to be used:

- a) Two common piezometer fittings.
- b) A meter nozzle barrel on which calibrated meter nozzles are placed to measure water flow.
- c) A mercury gauge connected to the two piezometers to read the difference of pressure between the inlet and outlet ends of the hose.
- d) A water supply system capable of providing the required flow rates specified in Table 22.1.

## 22.4 Test method

22.4.1 The inlet and discharge ends of the sample are to be connected to the piezometer fittings. The discharge end is to be connected to a meter nozzle barrel on which the calibrated meter nozzles are placed. The pressure taps of the two piezometer fittings are to be connected by means of a hose to the mercury gauge. Water, at the appropriate flow rate specified in Table 22.1, is to be passed through the sample and readings of the mercury gauge are to be made. The mercury gauge readings are to be converted to values in psig or kPa per each 100 feet of hose.

## 23 Accelerated Aging Test of Threads

### 23.1 General

23.1.1 The breaking strength of the warp and filler threads that have been conditioned in an air-circulating oven as specified in 23.4.1 shall not be less than 40 percent of the strength of threads that have not been heated in air.

### 23.2 Sample

23.2.1 Six 8 inch (203 mm) long warp threads and six 8-inch long filler threads taken from the jacket or reinforcement of the hose are to be used.

### 23.3 Equipment

23.3.1 Breaking strength tests are to be conducted using a power-operated machine, as described in the Standard Test Methods for Vulcanized Rubber and Thermoplastic Rubbers and Thermoplastic Elastomers – Tension, ASTM D412. The Type II A oven described in the Standard Specification for Gravity – Convection and Forced-Ventilation Ovens, ASTM E145 is to be used for the conditioning.

### 23.4 Test method

23.4.1 Three warp threads and three filler threads are to be placed in an air-circulating oven at 165.0  $\pm$ 1.0°C (329.0  $\pm$ 1.8°F) for 168  $\pm$ 1/2 hours. After the conditioning, the threads are to rest for at least 24 hours in a room maintained at 23.0  $\pm$ 2.0°C (73.0  $\pm$ 3.6°F) and 50  $\pm$ 5 percent relative humidity. The threads are then to be subjected to a breaking strength test using a tensile-strength testing machine having a jaw separation of 2 inches (50.8 mm) per minute. The average of three samples is to be considered the breaking strength. This value is to be compared with the average breaking strength of the three warp and three filler thread samples that have not been heated in air.

## 24 Adhesion Tests

### 24.1 General

24.1.1 The adhesion between the lining and the jacket or reinforcement shall be such that the rate of separation of a 1-1/2 inch (38.1 mm) strip of the lining from the jacket or reinforcement shall not be greater than 1 inch (25.4 mm) per minute when a weight of 12 pounds (5.4 kg), is applied in accordance with 24.3.1 – 24.4.2.

24.1.2 If a rubber backing is used between the lining and the jacket or reinforcement, the adhesion between the lining and the backing and between the backing and the jacket or reinforcement shall be such that the rate of separation of a 1-1/2 inch (38.1 mm) strip is not greater than 1 inch (25.4 mm) per minute when a weight of 12 pounds (5.4 kg) is applied. See 24.4.2.

24.1.3 The requirements of 24.1.1 and 24.1.2 are not intended to exclude a construction that provides no adhesion between the jacket and lining along the fold, if the surface over which there is no adhesion is not greater than 35 percent of the total surface.

24.1.4 The adhesion between the cover and the woven jacket or reinforcement shall be such that the rate of separation of a 1-1/2 inch (38.1 mm) strip of the cover from the jacket or reinforcement shall not be greater than 1 inch (25.4 mm) per minute with a weight of 10 pounds (4.5 kg).

## 24.2 Sample

24.2.1 The sample is to be 2 inches (50.8 mm) wide and is to be cut through to give a rectangular sample 2 inches wide and the full circumference of the hose in length. A strip of lining or cover 1-1/2 inches (38.1 mm) wide is to be cut out accurately; the cut is to extend through the lining or cover but not entirely through the woven jacket or reinforcement. This strip is to be separated from the jacket for about 1-1/2 inches. A reference mark is to be placed on the jacket or reinforcement at the juncture of the jacket or reinforcement or cover.

## 24.3 Equipment

24.3.1 A supporting frame, clamps, weights, weight holders, and a timer are to be used. The supporting frame is to be constructed so that the sample, with weights attached, may be suspended vertically and hang freely during the duration of the test.

## 24.4 Test method

24.4.1 With the separated jacket or the reinforcement, or the reinforcement together with the cover or lining, gripped in a stationary clamp, the separated lining or cover is to be gripped in a freely suspended clamp hanging vertically, to which the prescribed weight is to be attached. Provisions are to be made for supporting and releasing the weight slowly without jerking. The distance through which separation takes place is to be noted for 10 minutes, or until complete separation occurs. The adhesion to the jacket or reinforcement is to be taken as the rate obtained by dividing the total distance separated in inches (mm), to the nearest 0.1 inch (2.5 mm), by the elapsed time in minutes.

24.4.2 If a rubber backing is used between the lining and the jacket or reinforcement, the adhesion between the lining and the backing and the adhesion between the backing and the jacket or reinforcement are to be determined using the methods described in 24.4.1. If the adhesion between the lining and the backing or between the backing and the jacket or reinforcement cannot be determined because the backing has a tendency to tear during the test, the rate of separation between the separating members is to be considered the adhesion.

## 25 Accelerated Aging Test of Linings and Covers

### 25.1 General

25.1.1 The tensile strength and ultimate elongation of specimens of a lining and cover, if any, that have been conditioned for  $70 \pm 1/2$  hours in an air oven at  $100.0 \pm 1.0^\circ\text{C}$  ( $212.0 \pm 1.8^\circ\text{F}$ ) shall not be less than 80 percent of the tensile strength and 50 percent of the ultimate elongation of specimens that have not been heated in air.

## 25.2 Sample

25.2.1 Six samples, each approximately 1 inch wide, of the lining and cover are to be cut transversely from a representative section of the hose. The test specimens described in 25.4.5 are to be obtained from these cut sections.

## 25.3 Equipment

25.3.1 Tensile strength and elongation tests are to be conducted using a power-driven machine as described in the Standard Test Methods for Vulcanized Rubber and Thermoplastic Rubbers and Thermoplastic Elastomers – Tension, ASTM D412.

25.3.2 The rate of travel of the power-actuated grip is to be  $20 \pm 1$  inches ( $508 \pm 25.4$  mm) per minute.

25.3.3 The elongation is to be measured by means of a scale or other device capable of indicating the elongation with an accuracy of 0.1 inch (2.5 mm) without damaging the specimens.

25.3.4 For removing irregularities in samples, the buffing machine or skiving machine outlined in the Standard Practice for Rubber – Preparation of Pieces for Test Purposes from Products, ASTM D3183, be used.

25.3.5 Die C and the dial micrometer described in the Standard Test Methods for Vulcanized Rubber and Thermoplastic Rubbers and Thermoplastic Elastomers – Tension, ASTM D412, are to be used for cutting and measuring the thickness of the specimens.

25.3.6 The Type II A oven described in the Standard Specification for Gravity – Convection and Forced-Ventilation Ovens, ASTM E145, is to be used for the conditioning.

## 25.4 Test method

25.4.1 Tensile strength and ultimate elongation are to be determined in accordance with Method A of the Standard Test Methods for Vulcanized Rubber and Thermoplastic Rubbers and Thermoplastic Elastomers – Tension, ASTM D412. Three specimens for oven conditioning and three specimens for comparison purposes are to be prepared as described in 25.4.2 – 25.4.7.

25.4.2 The parts to be tested are to be separated from the hose jacket or reinforcement without the use of solvent, if practicable, and without excessive stretching of the parts. If it is necessary to use a solvent, commercial isoctane is to be used. The separated part is then to be placed so as to permit free evaporation of the solvent from the part for at least 1 hour before testing.

25.4.3 The samples of the lining and cover are to be buffed or skived prior to die-cutting to remove unevenness of surface or backing, if used, that would interfere with an accurate measurement of the specimen thickness. If the nature or thickness of the lining or cover is such that buffing or skiving cannot be accomplished without damaging the lining or cover, any of the following procedures are acceptable:

- a) Determine tensile strength and elongation on specimens with no prior buffing or skiving, using the dial micrometer specified in 25.3.5, an optical micrometer, or an optical comparator to determine thickness.
- b) Determine tensile strength and elongation on specimens obtained from cured slabs of the material.

25.4.4 If the lining and cover are made from the same material, specimens for the tensile strength and elongation tests may be obtained from either component, and the results are to be considered representative of both components.

25.4.5 After buffing or skiving, dumbbell specimens are to be die-cut and have a constricted portion 0.25 inch (6.4 mm) wide and 1.3 inches (33.0 mm) long. The enlarged ends are to be 1 inch (25.4 mm) wide.

25.4.6 Three measurements for thickness are to be made in the constricted portion of each specimen. The minimum value obtained is to be used as the thickness of the specimen in calculating the tensile strength. The average tensile strength and elongation of three specimens is to be considered the tensile strength and elongation.

25.4.7 If an automatic extensometer is not used, two parallel bench marks for use in determining elongation are to be placed centrally 1 inch (25.4 mm) apart on the constricted portion of each of three samples. Care is to be taken not to injure the specimen. The 1-inch bench marks, if used, are to be placed on the other three specimens after conditioning. The specimens are to be conditioned as specified in 25.1.1 and tested in accordance with the test procedures specified in Standard Test Method for Rubber-Deterioration in an Air Oven, ASTM D573. The tensile strength and ultimate elongation of the aged specimens are to be compared with the tensile strength and elongation of specimens that have not been heated in air.

25.4.8 Results of tests of specimens that break in the curved portion may be acceptable if the measured strength and elongation values are at least equal to those for specimens that break within the bench marks. If such results are not obtained, the test is to be repeated with new specimens.

## 26 Ozone-Exposure Test of Linings and Covers

### 26.1 General

26.1.1 For hose and hose assemblies intended to be marked as ozone resistant in accordance with 38.2.3, the linings and covers shall show no visible signs of cracking when stressed and exposed for 70  $\pm$ 1/2 hours to an atmosphere having an ozone partial pressure of 100  $\pm$ 10 mPa at a temperature of 40.0  $\pm$ 1.0°C (104  $\pm$ 1.8°F).

### 26.2 Sample

26.2.1 Three specimens, 3-3/4 inches (95.3 mm) long by 1 inch (25.4 mm) wide, cut from the lining and cover of a representative sample are to be used for this test.

## 26.3 Equipment

26.3.1 The ozone test chamber for this test is to be as described in the Standard Test Method for Rubber Deterioration – Surface Ozone Cracking in a Chamber, ASTM D1149. The specimen holder is to be as described in Procedure B of the Standard Test for Rubber Deterioration – Surface Cracking, ASTM D518.

## 26.4 Test method

26.4.1 The three specimens are to be cut longitudinally from the lining and cover of the sample and mounted in the specimen holder in a looped position in accordance with the procedures outlined in Procedure B of the Standard Test for Rubber Deterioration – Surface Cracking, ASTM D518. The waterway surface of the lining specimens and the outer surface of the cover are to be on the outside of the looped specimen. The ozone test chamber is to be regulated to provide an ozone partial pressure of  $100 \pm 10$  mPa and a temperature of  $40.0 \pm 1.0^\circ\text{C}$  ( $104.0 \pm 1.8^\circ\text{F}$ ). When constant test conditions have been obtained in the ozone chamber and after the mounted specimens have remained in an ozone free atmosphere for 24 hours, the mounted specimens are to be placed in the test chamber for 70 hours. After exposure, the specimens are to be removed from the test chamber and visually examined with a 7-power hand magnifying glass while still mounted in the specimen holder.

## 27 Water Immersion Test of Linings

### 27.1 General

27.1.1 The tensile strength, ultimate elongation, and volume change of a lining shall comply with the requirements specified in items a – c after immersion for  $168 \pm 1/2$  hours in distilled or deionized water at a temperature of  $70.0 \pm 1.0^\circ\text{C}$  ( $158.0 \pm 1.8^\circ\text{F}$ ).

- a) Minimum retention of tensile strength – 75 percent.
- b) Minimum retention of ultimate elongation – 75 percent.
- c) Maximum volume swell – 25 percent.

### 27.2 Sample

27.2.1 Six tensile strength and elongation specimens are to be prepared from the lining, as described in 25.4.2 – 25.4.8, and three volume change specimens, 2 inches (50.8 mm) long by 1 inch (25.4 mm) wide, are to be cut from the lining of a representative section of hose.

### 27.3 Equipment

27.3.1 A water or oil bath or oven capable of maintaining the test liquid at  $70.0 \pm 1.0^{\circ}\text{C}$  ( $158.0 \pm 1.8^{\circ}\text{F}$ ) is to be used for this test.

27.3.2 The equipment for the tensile strength and ultimate elongation determinations is to be as described in 25.3.1 – 25.3.5.

27.3.3 An analytical balance provided with a bridge for the support of a vessel of distilled or deionized water and a metal die for cutting rectangular specimens 1 by 2 inches (25.4 to 50.8 mm) are to be used.

### 27.4 Method – Effect on tensile strength and ultimate elongation

27.4.1 For the tensile strength and ultimate elongation determinations, six specimens of the lining are to be prepared in the same manner as for tensile strength and elongation tests described in 25.4.2 – 25.4.7 before immersing the specimens in the test liquids, except that 1 inch (25.4 mm) apart marks are to be placed on the specimens after the immersion unless an automatic extensometer is used. The specimens are to be immersed in such a manner that they do not touch each other or the sides of the container. Three tube specimens are to be immersed for 168 hours in distilled or deionized water. The water is to be maintained at  $70.0 \pm 1.0^{\circ}\text{C}$  ( $158.0 \pm 1.8^{\circ}\text{F}$ ) throughout the immersion period. At the end of the immersion period, the specimens that had been immersed are to be cooled for 30 to 60 minutes in new test liquid maintained at  $23.0 \pm 2.0^{\circ}\text{C}$  ( $73.4 \pm 3.6^{\circ}\text{F}$ ). Immediately upon removal from the liquid maintained at  $23.0 \pm 2.0^{\circ}\text{C}$ , the specimens are to be blotted dry with a soft cloth or filter paper, the 1 inch bench marks (if an automatic extensometer is not used) are to be placed on the specimens, and the specimens are to be subjected to tensile strength and elongation tests in accordance with Method A of the Standard Test Methods for Vulcanized Rubber and Thermoplastic Rubbers and Thermoplastic Elastomers – Tension, ASTM D412. For comparative purposes, three specimens of the lining that have not been immersed in the test liquid are to be subjected to tensile strength and elongation tests.

### 27.5 Method – Effect on volume

27.5.1 For the volumetric swelling determinations, samples from the lining of the hose are to be buffed or skived smooth, and three specimens are to be cut by means of the die, see 25.3.5. The volume of each specimen is to be determined by weighing it first in air and then in water. The specimens are then to be immersed for 70 hours in distilled or deionized water. The water is to be maintained at  $70.0 \pm 1.0^{\circ}\text{C}$  ( $158.0 \pm 1.8^{\circ}\text{F}$ ) throughout the immersion period. At the end of the immersion period, the specimens are to be cooled for 30 to 60 minutes in new test liquid maintained at  $23.0 \pm 2.0^{\circ}\text{C}$  ( $73.4 \pm 3.6^{\circ}\text{F}$ ). The specimens are then to be removed one at a time from the water, rinsed in ethyl alcohol, blotted dry with a soft cloth or filter paper, and again weighed, first in air and then in water. The weight in air is to be taken within 30 seconds after the specimen is removed from the test liquid, and the weight in water is to be taken within 60 seconds after removal from the test liquid. The percent increase in volume is to be calculated for each specimen and the results for the three specimens are to be averaged.

## 28 Pull Test

### 28.1 General

28.1.1 The couplings of a hose assembly shall not be mechanically damaged at the threaded or swivel connections and shall not move or separate from the hose when subjected to a pull of not less than 1200 pounds-force (8.9 kN) times the diameter of the hose in inches ( $\text{mm} \times 0.039$ ).

### 28.2 Sample

28.2.1 A  $10 \pm 2$  inch ( $254 \pm 51$  mm) length of hose assembly is to be used.

### 28.3 Test method

28.3.1 The male and female ends of the coupling are to be attached to threaded male and female adapters that, in turn, are to be fitted for installation in the testing machine.

28.3.2 The tension applied to the sample is to be at the rate of 0.1 inch (2.5 mm) per minute up to the value specified in 28.1.1.

## 29 Accelerated Aging Test of Hose Assembly

### 29.1 General

29.1.1 The couplings of a hose assembly that have been conditioned for  $70 \pm 1/2$  hours in an air-circulating oven at  $100.0 \pm 1.0^\circ\text{C}$  ( $212.0 \pm 1.8^\circ\text{F}$ ) shall not separate from the hose when subjected to the pull specified in 28.1.1.

### 29.2 Sample

29.2.1 The length of the sample is to be  $10 \pm 2$  inches ( $254 \pm 51$  mm).

### 29.3 Equipment

29.3.1 The equipment specified in 25.3.6 is to be used.

## 29.4 Test method

29.4.1 The sample is to be conditioned as specified in 29.1.1. After the conditioning, the sample is to be subjected to the Pull Test, Section 28.

## 30 Rough Usage Test

### 30.1 General

30.1.1 A complete assembly of mating couplings connected together, unattached to hose, and a coupling with a swivel shall not be deformed or damaged to such an extent that the swivel mechanism cannot be turned by the exertion of a torque of 100 pounds-feet (136 N·m) or less after being subjected to the drop tests described in 30.4.1 and 30.4.2.

### 30.2 Sample

30.2.1 Three assemblies of mating couplings connected together and three couplings with swivels in each size are to be used.

### 30.3 Equipment

30.3.1 A torque wrench having a minimum force of 100 pounds-feet (136 N·m) is to be used.

### 30.4 Test method

30.4.1 Each sample is to be dropped three times from a height of 6 feet (1.8 m) onto a concrete surface in such a manner as to impact on the swivel portion of the coupling. The drop height is to be measured from the concrete surface to the lowest edge of the sample. Each sample is then to be examined for cracks, broken sections, distortion, and binding.

30.4.2 If the samples show distortion or binding of the swivel mechanism, the force required to turn the swivel mechanism is to be measured.

## 31 Moist Ammonia-Air Stress Cracking Test

### 31.1 General

31.1.1 After being subjected to the conditions described in 31.3.1 – 31.4.2 a brass part containing more than 15 percent zinc shall show no evidence of cracking when examined using 25X magnification.

## 31.2 Sample

31.2.1 A coupling or component in each size connected to a 6 inch (152 mm) length of hose in accordance with the manufacturer's instructions and then to an appropriate mating coupling tightened to the minimum torque necessary to produce a leaktight assembly is to be used.

## 31.3 Equipment

31.3.1 The equipment is to consist of a glass chamber approximately 12 by 12 by 12 inches (305 by 305 by 305 mm), a glass cover, aqueous ammonia having a specific gravity of 0.94, an inert grid to support samples 1-1/2 inches (38.1 mm) above solution, and an oven or water bath capable of maintaining a temperature of  $34.0 \pm 2^\circ\text{C}$  ( $93 \pm 3.6^\circ\text{F}$ ).

## 31.4 Method

31.4.1 Each test sample is to be subjected to the physical stresses normally imposed on or within a part as the result of assembly with other components. Such stresses are to be applied to the sample prior to and maintained during the test. Threaded parts are to be engaged to an appropriate mating coupling and tightened to the minimum torque required to produce a leaktight assembly. Teflon® tape or pipe thread compound are not to be used on the threads.

31.4.2 Three samples are to be degreased and then continuously exposed in a set position for 240 hours to a moist ammonia-air mixture maintained in a glass chamber 12 by 12 by 12 inches (305 by 305 by 305 mm) having a glass cover. 600 ml of aqueous ammonia having a specific gravity of 0.94 are to be maintained at the bottom of the glass chamber below the samples. The samples are to be positioned 1-1/2 inches (38.1 mm) above the solution and supported by an inert grid. The glass chamber, with the cover in place, is then to be placed in an oven or water bath maintained at a temperature of  $34.0 \pm 2^\circ\text{C}$  ( $93 \pm 3.6^\circ\text{F}$ ) for 240 hours.

## 32 Salt-Spray Corrosion Test

### 32.1 General

32.1.1 A coupling assembly having metallic parts of materials other than high strength, yellow brass, UNS No. C86500 in the Standard Specification for Copper Alloys in Ingot Form, ASTM B30, and in the Standard Specification for Copper Alloy Sand Castings for General Applications, ASTM B584, shall be subjected to the salt spray exposure as described in 32.4.1. After the exposure and drying, the torque required to disassemble the coupling assembly shall not be greater than 100 pounds-feet (136 N·m). If there is evidence of galvanic corrosion between dissimilar metals, the exposed couplings shall be connected to the type of hose for which they are intended to be used, and the hose assembly while lying straight, shall comply with the requirements in 13.1.1.

## 32.2 Sample

32.2.1 Samples are to include two assemblies in each size, each consisting of mating couplings, and two couplings of each design connected to mating couplings of brass as described in 32.1.1. The samples are to be tightened together with the minimum torque necessary to produce a leaktight assembly.

## 32.3 Equipment

32.3.1 The equipment described in Standard Practice for Operating Salt-Spray (Fog) Apparatus, ASTM B117, is to be used. A torque wrench having a minimum force of 100 pounds-feet (136 N·m) is also to be used.

## 32.4 Test method

32.4.1 Uncoated sample couplings are to be subjected to the salt spray exposure for 10 days in accordance with the methods specified in Standard Practice for Operating Salt-Spray (Fog) Apparatus, ASTM B117.

32.4.2 Samples that are coated for corrosion protection are to be preconditioned by being assembled with a torque of 50 pounds-feet (67.8 N·m) and then disassembled for a total of 50 assemble-disassemble cycles. The couplings are then to be assembled and subjected to the salt spray exposure for 10 days in accordance with the methods specified in Standard Practice for Operating Salt-Spray (Fog) Apparatus, ASTM B117.

## 33 Accelerated Aging Test of Gaskets

### 33.1 General

33.1.1 The tensile strength and ultimate elongation of specimens of a gasket that have been conditioned for  $70 \pm 1/2$  hours in an air oven at a temperature of  $100.0 \pm 1.0^\circ\text{C}$  ( $212.0 \pm 1.8^\circ\text{F}$ ) shall not be less than 80 percent of the tensile strength and 50 percent of the elongation of specimens that have not been conditioned.

### 33.2 Sample

33.2.1 Three straight specimens are to be obtained from the circumference of the gasket. In order to reduce the amount of buffing or skiving, gaskets may be cut around the circumference with a sharp knife or razor blade. The irregularities are then to be buffed or skived until they are removed. The buffed or skived specimens are not to be greater than 0.075 inch (1.9 mm) thick.

### 33.3 Equipment

33.3.1 The equipment is to be as described in 25.3.1 – 25.3.6, except no cutting die is necessary.

### 33.4 Test method

33.4.1 Tensile strength and elongation are to be determined in accordance with the applicable portions of the methods described in 25.4.1 – 25.4.7.

## 34 Compression Set Test

### 34.1 General

34.1.1 The compression set of samples of a gasket material shall not exceed 20 percent of the original thickness after they have been compressed to 75 percent of the original thickness and then conditioned for  $22 \pm 1/2$  hours at a temperature of  $60.0 \pm 2.0^\circ\text{C}$  ( $140.0 \pm 3.6^\circ\text{F}$ ).

### 34.2 Samples

34.2.1 Type I samples of the gasket material are to be prepared as described in Method B of the Standard Test Methods for Rubber Property – Compression Set, ASTM D395.

### 34.3 Equipment

34.3.1 The oven described in 23.3.1 and equipment as described in Method B of the Standard Test Methods for Rubber Property – Compression Set, ASTM D395 are to be used.

### 34.4 Test method

34.4.1 The test method is to be as described in Method B of the Standard Test Methods for Rubber Property – Compression Set, ASTM D395.

## 35 Ozone Resistance Test of Gaskets

### 35.1 General

35.1.1 For hose assemblies intended to be marked as ozone resistant in accordance with 38.2.3, the gasket of a coupling shall show no visible signs of cracking when stressed and exposed for  $70 \pm 1/2$  hours to an atmosphere having an ozone partial pressure of  $100 \pm 10$  mPa at a temperature of  $40.0 \pm 1.0^\circ\text{C}$  ( $104.0 \pm 1.8^\circ\text{F}$ ).

## 35.2 Sample

35.2.1 Three straight specimens, 3-3/4 inches (95.3 mm) in length, are to be obtained from the circumference of the gasket. In order to reduce the amount of buffing, gaskets may be cut around the circumference with a sharp knife or razor blade. The specimens are to be buffed smooth and uniform until the thickness is 0.075 to 0.100 inches (1.9 to 2.5 mm).

## 35.3 Equipment

35.3.1 The equipment is to be as described in 26.3.1.

## 35.4 Test method

35.4.1 The test method is to be as described in 26.4.1. The specimens are to be exposed to ozone while bent in the direction of the natural curvature.

## 36 Water Immersion Test of Gaskets

### 36.1 General

36.1.1 The tensile strength, ultimate elongation, and volume change of the gasket of a coupling shall comply with the Water Immersion Test of Linings, Section 27.

### 36.2 Sample

36.2.1 Specimens obtained from representative gaskets as described in 33.2.1 are to be used for the tensile strength and ultimate elongation measurements. Specimens obtained from representative gaskets and approximately 2 inches long (50 mm) by the width or thickness of the gasket are to be used for volume change measurements.

## MANUFACTURING AND PRODUCTION TESTS

### 37 General

37.1 To determine compliance with these requirements in production the manufacturer shall provide the necessary production control, inspection, and tests.

37.2 Each hose shall be subjected to the proof pressure test specified in 11.1.1(b).

37.3 The manufacturer is to furnish all necessary equipment and facilities for determining compliance with the requirements, including a pressure gauge, and the like. Provision is to be made for calibrating the pressure gauge as often as may be necessary to verify that it is accurate; but at least once every 3 months, the manufacturer shall calibrate each gauge used in the test work and record the readings.

## MARKING

### 38 Details

#### 38.1 General

38.1.1 If a manufacturer produces hose or hose assemblies at more than one factory, each length of hose shall have a distinctive marking to identify it as the product of a particular factory.

#### 38.2 Hose

38.2.1 Each length of hose shall be indelibly marked in letters and figures at least 1 inch (25.4 mm) high with the following:

- a) Manufacturer's name or coded designation.
- b) Trade name or hose designation.
- c) Month or quarter and year of manufacture.
- d) The words "Service Test to \_\_\_ psig (kPa)," where \_\_\_\_\_ is the appropriate pressure.

38.2.2 Hose complying with the requirements in 20.1.2 may be marked "For Use Down To minus 65°F (minus 54°C)."

38.2.3 Hose complying with the requirement in 26.1.1 may be marked "Ozone Resistant."

38.2.4 The markings specified in 38.2.1 shall start at 3.5 – 4.5 feet (1.1 – 1.4 m) from both ends of each length of the hose.

#### 38.3 Hose Assemblies

38.3.1 Each coupling of hose assemblies shall be marked with the following information using stamped or cast figures and letters not less than 3/16 inch (4.8 mm) high:

- a) Name or identifying symbol of the assembly manufacturer.
- b) Distinctive catalog or model designation.
- c) Type of thread.

38.3.2 The hose of each coupled hose assembly shall be marked in accordance with 38.1.1 – 38.2.4.

No Text on This Page

Document Was Downloaded By YAHFEI WHATI10119  
For Use By YAH FEI ELECTRIC LIGHTING CO LTD  
14083 : 6/9/2007 - 10:35 PM  
UL COPYRIGHTED MATERIAL –  
NOT AUTHORIZED FOR FURTHER REPRODUCTION OR  
DISTRIBUTION WITHOUT PERMISSION FROM UL